

# CM 100 Gypsos

EASY TO USE

PUMPABLE

CM 100 Gypsos is a pumpable, gypsum based self-levelling underlayment.

June 14, 2019

## Area of use

The product is suitable for new construction and renovation. The product is intended for indoor use on substrates of concrete, lightweight concrete, stone, ceramic tiles gypsum underlay, wood and homogeneous PVC. The product is intended to be covered with a top layer, e.g. tiles, carpets or similar.

## Pre-treatment

The substrate should be clean and free of dust, cement skin, grease and other impurities that can prevent adhesion. Adhesion and surface strength of the substrate should be no less than 0.5 MPa. If the substrate is weaker than 0,5 MPa, a test should be executed. The test should be applied on 0,5x3,0 meters and evaluated after 3 days for any cracks. Contact Combimix for consultation. Always prime the underlying substrate with PP 600 and allow to dry before pouring. In terms of the primer forming a film, the temperature of the substrate must not fall below 10 °C. For best results, the ambient temperature in the work area should be between 10 and 25 °C. At higher or lower temperatures, the time for curing will shorten or extend. With the risk for cracks due to shrinkage or settings in the subfloor, a concrete surface should not be leveled within the first 28 days after casting. As a recommendation the RH in the concrete should have reached RH 90 % as the upper limit for pouring the CM 100. Use the Combimix form foam for edging. In order to avoid drainage pipes from getting clogged, always make sure the drains are properly sealed before pouring.


## Mixing

Mix the dry powder with max 3.8 liters of water (max 19 %) per 20 kg bag. Mix with a drilling machine and a whisk, or a mixing pump intended for this purpose. The correct water mixture can be tested using a slump test with a cylinder with Ø 30 mm and a height of 50 mm on 300 x 300 mm plexiglas plate. With the correct water mixture, the spread should be max 140 mm. The slump test also checks that the material is well blended and that there is no separation.


## Application




Water requirements  
3.8 l/20 kg



Working time  
10–20 min




Workplace temperature  
10–25 °C



Thickness  
5–50 mm



Final set  
1–3 hrs



Coverable (tiles)  
12 hrs



# CM 100 Gypsos

EASY TO USE

PUMPABLE

CM 100 Gypsos is a pumpable, gypsum based self-levelling underlayment.

June 14, 2019

The mixed material is applied by hand, or pumped out onto the substrate in lengths. Each new ribbon is added to the old one as soon as possible so that the material can blend together and create an even surface. The width of the ribbons can be adjusted to the capacity of the mixing pump and the thickness of the covering. The material requires a light treatment with a toothed trowel to provide maximum smoothness.

## Post-treatment and curing

You can easily shape or cut the semi-hardened self-leveling underlayment material before it fully dries. Always make sure that the material is sufficiently dry before it will be covered by a carpet or a foilsystem. The guided time for dehydration down to RH 90 % of the product is 10 mm per week. The guiding value assumes a curing temperature of approximately 20 °C, 40 % RH and proper air flow.

## Storage time and packaging

Store in a dry environment, on an unopened plastic-coated pallet, six months from the date of production. The date of production is printed on the packaging. May be used after 6 months but properties such as flow rate, hardening and drying times will be extended. CM 100 Gypsos is delivered in 20 kg bags and in big bags.

## Residual products and safety information

Empty bags can be burned. Any remaining, dry powder that has been stored properly can be used again. Hardened material should be disposed of as construction waste. Do not wash the product into the sewage system. The cement in the product has a reduced level of chromate. Follow regulations in each respective country.

## Health, environment, safety and technical service documents

For current version of product information, contact Combimix at [info@combimix.se](mailto:info@combimix.se). Previously undated and dated issues are no longer valid. For more information contact our sales organization.

This product sheet contains general information. Products can be used in a number of changing conditions and situations. Combimix is not responsible for the storage, use in construction, processing or design, interactions with other products, required use due to local conditions or other external factors. Combimix is also not responsible for cases where the above information has been misinterpreted or neglected by the user.



# CM 100 Gypsos

EASY TO USE

PUMPABLE

CM 100 Gypsos is a pumpable, gypsum based self-levelling underlayment.

June 14, 2019

## Produktspecifikation

Release of corrosive substances	CA (as per EN 13813)
Compressive strength class	C20 (as per EN 13813)
Compressive strength average	20 MPa (as per EN 13813)
Flexural strength class	F5 (as per EN 13813)
Flexural strength average	5 MPa (as per EN 13813)
Fire resistance class	A1fl (as per EN 13813)
Thickness	5–50 mm
Thickness	6–20 mm on lightweight concrete
Grain size	< 2 mm
Material consumption	1,7 kg/m <sup>2</sup> /mm
Weight (dry state)	1700 kg/m <sup>3</sup>
Water requirements	3.8 l/20 kg
Flow rate	max 140 mm
Workplace temperature	10–25 °C
Mixing time	3 min
Working time	10–20 min
Final set	1–3 hrs
Coverable (tiles)	12 hrs
Carpetable	10 mm/week
pH	approx. 11
Water damage resistant	yes
Surface Tensile Bond Strength, 28 days (sanded, loaded surface)	> 1,5 MPa
Shrinkage	0–0,01 %
TVOC 28 days	< 10 µg/(m <sup>2</sup> h)

